



# Clear Epoxy Resin U1030

A modified Epoxy and polyamine Hardner with low viscosity and super transparent liquid to reinforcement type of Wooden surfaces and stone slabs. This product has a good resistance to yellowing.

---

---

## PART A

Property	Value	Unit of meausurment
Viscosity at 25°C	1200-1500	C.P
COLOR	Max 0.5	Gardner
EEW	185-194	gr/eq

## PART B

Property	Value	Unit of meausurment
Viscosity @ 25°C	150-170	C.P
COLOR	Max 0.3	Gardner
H-active equivalent	90-98	g/mol
Gel Time @ 25°C	40	Min.

\*These values provide general information and are not part of the product specification.

Shelf life: in sealed containers **Technical Datasheet**

\* Mixing Ratio is 1:2



### **Safety Consideration**

Recommended to use Protective Gloves, Eye protection, Full filter Mask during work with this product.

### **Packing**

This product available in 200Kg Iron drum, 20Kg and 5Kg Polyethylene drums.

### **Shelf life**

Recommended shelf life time in sealed containers at room temperature & away of sunlight is one year.