



Technical Datasheet

Clear Epoxy Resin U1030

A modified Epoxy and polyamine Hardner with low viscosity and super transparent liquid to reinforcement type of Wooden surfaces and stone slabs. This product has a good resistance to yellowing.

PART A

Property	Value	Unit of meausurment
Viscosity at 25°C	1200-1500	C.P
COLOR	Max 0.5	Gardner
EEW	185-194	gr/eq

PART B

Property	Value	Unit of meausurment
Viscosity @ 25°C	150-170	C.P
COLOR	Max 0.3	Gardner
H-active equivalent	90-98	g/mol
Gel Time 100g @ 25°C	75	Min.

*These values provide general information and are not part of the product specification.

Shelf life: in sealed containers at room temperature, one year.

* **Mixing Ratio is 1:2**



Technical Datasheet

Safety Consideration

Recommended to use Protective Gloves, Eye protection, Full filter Mask during work with this product.

Packing

This product available in 200Kg Iron drum, 20Kg and 5Kg Polyethylene drums.

Shelf life

Recommended shelf life time in sealed containers at room temperature & away of sunlight is one year.